

## 70% ALUMINA BALL/LINING SPECIFICATIONS

### ■ TECHNICAL DATA

Items	70% Alumina Ball/Lining
Al <sub>2</sub> O <sub>3</sub> Content	≥ 70.00 %
SiO <sub>2</sub>	< 25.00 %
Fe <sub>2</sub> O <sub>3</sub>	< 1.50 %
NaO	< 1.00 %
Density (g/cm <sup>3</sup> )	≥ 3.00
Wear loss	0.2‰ ~ 0.3‰
Hardness	8 mohs
Color	White grey

### ■ CONTENT ANALYSIS

ITEM	UNIT	DATA
SiO <sub>2</sub>	%	22.40
Fe <sub>2</sub> O <sub>3</sub>	%	1.35
Al <sub>2</sub> O <sub>3</sub>	%	70.29
TiO <sub>2</sub>	%	2.22
CaO	%	1.06
MgO	%	0.91
Other	%	1.23
Total	%	100.00

---

### TOAN PHAT INDUSTRIAL CORP

29 Ha Huy Giap str, Thanh Loc Ward, Dist 12<sup>th</sup>, Ho Chi Minh City, Vietnam

TEL: 08-3716 0639/0727 FAX: 08-6256 3289 Homepage: [www.toanphatchemicals.com](http://www.toanphatchemicals.com) E-Mail: [globalchems@yahoo.com](mailto:globalchems@yahoo.com)