



中国淄博奥罗拉陶瓷科技有限公司

CHINA ZIBO AOKEROLA CERAMIC TECHNOLOGY CO., LTD.

93% ALUMINA BALL/LINING SPECIFICATIONS

■ TECHNICAL DATA

Items	93% Alumina balls/Lining
Al ₂ O ₃ Content (%)	≥ 93
Rate of Water Absorption (%)	≤ 0.01
Specific Gravity (g/cm ³)	3.64 ~ 3.67
Hardness (Mohs Scale)	9
Anti-Compression Strength (MPa)	≥ 2000
Color	White
Equivalent Wear Loss	≤ 0.08‰

■ 92% ALUMINA BALLS/LINING

ITEM NAME	UNIT	DATA
SiO ₂	%	4.30
Fe ₂ O ₃	%	0.04
Al ₂ O ₃	%	93.05
TiO ₂	%	0.05
CaO	%	1.09
MgO	%	0.66
K ₂ O	%	0.08
Na ₂ O	%	0.33
OTHERS	%	0.40

TOAN PHAT INDUSTRIAL CORP

29 Ha Huy Giap str, Thanh Loc Ward, Dist 12th, Ho Chi Minh City, Vietnam

TEL: 028-3716 0639/0727 FAX: 028-6256 3289 Homepage: www.toanphatchemicals.com E-Mail: globalchems@yahoo.com