

TECHNICAL DATA SHEET
Petroleum Resin GA 120

Production Name	Petroleum Resin	
Production Code	GA 120	
Production's Analysis		
Description	Standard	Test Method
Color No (50% Toluene)	#12 Max	ASTM D 1544
Softening Point	120°C ± 5°C	ASTM E 28
Acid Value	0.10 Max (KOH mg/g)	ASTM D 974
Bromine Value	25 Max (gBr/100g)	ASTM D 1159
Specific Gravity (25 ⁰ C)	1.05-1.10	ASTM D 71
Appearance	Granular solid form	Eyeballing
Origin	Taiwan (YUEN LIANG)	
Application	Alkyd paint, Adhesive solvent base, cold set ink	