

TECHNICAL DATA SHEET

 NC DAMPING WITH EA
 H 1/8

Item	Index		
	Unit	H1/8"	Test Method
Nitrogen Cont	%	11.8~12.2	WJ 9028-05 4.5.2
Viscosity	Sec	1.7~2.2 (C法)	WJ 9028-05 4.5.3
Acid CON.	%	≤0.06	WJ 9028-05 4.5.7
Damping agent	%	30±2	WJ 9028-05 4.5.12
Water	%	≤6	KARL FICHER
Solubility	—	Clear	Visible
Appearance		White soft fiber	Visible
Ash	%	≤0.2	WJ 9028-05 4.5.10
Abel 80°C	Mins	≥15	WJ 9028-05 4.5.8
Ignition point	°C	≥180	WJ 9028-05 4.5.9